

No English title available.

Patent Number: ☐ DE10049257

Publication date: 2001-04-26

Inventor(s): LEE SANG-IN (KR); CHOI SUNG-JE (KR); KIM YEONG-KWAN (KR); LIM JAE-SOON (KR); PARK YOUNG-WOOK (KR)

Applicant(s): SAMSUNG ELECTRONICS CO LTD (KR)

Requested Patent: ☐ JP2001152339

Application Number: DE20001049257 20001005

Priority Number(s): KR19990043056 19991006; KR19990050902 19991116; KR20000014824 20000323; KR20000053415 20000908

IPC Classification: C30B33/00; H01L21/316

EC Classification: H01L21/316, C30B25/02, H01L21/316D

EC Classification: H01L21/316; C30B25/02+29/20; H01L21/316D

Equivalents: CN1292431, ☐ GB2355727

(12) UK Patent Application (19) GB (11) 2 355 727 (13) A

(43) Date of A Publication 02.05.2001

(21) Application No 0024571.2

(22) Date of Filing 06.10.2000

(30) Priority Data

(31) 99043056	(32) 06.10.1999	(33) KR
(31) 99050902	(32) 16.11.1999	
(31) 00014824	(32) 23.03.2000	
(31) 00053415	(32) 08.09.2000	

(71) Applicant(s)

Samsung Electronics Co. Ltd.
(Incorporated in the Republic of Korea)
416 Maetan-dong, Paldal-gu, Suwon-City,
Kyungki-do 442-370, Republic of Korea

(72) and (74) continued overleaf

(51) INT CL⁷

C23C 16/44 14/00 14/08, H01L 21/316

(52) UK CL (Edition S)

C7F FCXE FHE FP905 FR908 FR914 F102 F251 F300
F302 F307 F802
U1S S2060

(56) Documents Cited

GB 2340508 A GB 2162862 A US 6090442 A
US 5374570 A US 4058430 A JP 110269652 A
& WPI Accession no 99-615894 JP010204434 A &
WPI Accession no 89-281185 JP010179423 A &
WPI Accession no 89-245666 Applied Physics Letters
Vol. 51, No. 15, 12 October 1987, pa s 1143-1145

(58) continued overleaf

(54) Abstract Title

Atomic layer deposition method

(57) In a method of forming a thin film using an atomic layer deposition (ALD) method, a thin film is formed on a substrate in a cycle of injecting a first reactant including an atom that forms the thin film and a ligand into a reaction chamber that includes the substrate, purging the first reactant, injecting a second reactant into the reaction chamber, and purging the second reactant. The thin film is formed by a chemical reaction between the atom that forms the thin film and a second reactant whose binding energy with respect to the atom that forms the thin film is larger than the binding energy of the ligand with respect to the atom that forms the thin film and the generation of by-products is prevented. The generation of a hydroxide by-product in the thin film is suppressed by using a material that does not include a hydroxide as the second reactant, purging the second reactant, and reacting the second reactant with a third reactant that includes hydroxide. After purging the second reactant, the third reactant for removing impurities and improving the stoichiometry of the thin film is injected and purged. By doing so, it is possible to obtain a thin film, which does not include impurities and whose stoichiometry is excellent. The dangling bond of the surface of the substrate is terminated by injecting oxidising gas before injecting the first reactant when the first reactant is $\text{Al}(\text{CH}_3)_3$ the second reactant is O_3 , O_2 , or N_2O . When the first reactant is a metal, the second reactant is N_2O , O_2 , O_3 , or CO_2 , and the third reactant is an oxidising gas.

FIG. 3





FIG. 5



GB 2 355 727 A